Specification Data Sheet

MP-2N



Pro-Formance[®]/MicroPore[®] Nonasbestos Gasket Material F729000M9

DESCRIPTION

MP-2N is specifically engineered for automotive powertrain, marine and small engine applications. It provides exceptional sealability for coolant, lubrication, and induction systems. It conforms well to irregular flange surfaces and is intended for applications with short duration maximum temperatures up to 205°C (400°F).

SPECIFICATION PROPERTIES

Property	Value	Method
Density, g/cc(lb/cu.ft)	1.35 (84) (min.)	ASTM F 1315
Compressibility, % (at 34.5MPa)	13 - 25	ASTM F 36
Recovery, %	35 (min.)	ASTM F 36
Tensile Strength, AMD, MPa(psi)	8.28 (1200) (min.)	ASTM F 152
Binder Type	Nitrile Butadiene	

REMARKS AND RELATED DOCUMENTS

Specification values determined by the test methods required for ASTM F-104, Type 7 materials.

EnCore[®], Hydro-Fused[®], MicroPore[®], Pro-Formance[®], Select-a-Seal[®], Syntheseal[®], Thermo-Tork[®], and Voltoid[®] are registered trademarks of Interface Solutions, Inc. Select-a-Shield is a trademark of Interface Solutions, Inc.

WARNING: The description and performance data provided herein constitute a material specification for quality control purposes, but do not imply suitability for use in a specific application. Your specific application should not be undertaken without independent study and evaluation for suitability. Failure to select proper sealing products may result in either property damage or personal injury. For specific application recommendations, contact Interface Solutions. INTERFACE SOLUTIONS EXPRESSLY DISCLAIMS ALL WARRANTIES EITHER EXPRESS OR IMPLIED, INCLUDING ANY IMPLIED WARRANTY OF MERCHANTABILITY OR OF FITNESS FOR A PARTICULAR PURPOSE. IN NO EVENT WILL ISI BE LIABLE FOR ANY INDIRECT, SPECIAL, INCIDENTAL, CONSEQUENTIAL OR PUNTIVE DAMAGES, HOWEVER CAUSED AND ON ANY THEORY OF LIABILITY, WHETHER IN CONTRACT, STRICT LIABILITY, OR TORT (INCLUDING NEGLIGENCE OR OTHERWISE) ARISING IN ANY WAY OUT OF THE USE OF THE INFORMATION CONTAINED IN ITS SPECIFICATION DATA SHEETS, ITS PRODUCTS OR THEIR FUTURE USE BY YOU OR ANY THIRD PARTIES, EVEN IF ADVISED OF THE POSSIBILITY OF SUCH DAMAGE. Alkegen

Headquarters 5215 N. O'Connor Blvd, Suite 2300 Irving, TX 75039 Telephone: 716-768-6500 Website: www.alkegen.com Email: info@alkegen.com

ALKEGEN

Form A-5776 Effective 02/25 © 2025 Alkegen All Rights Reserved