

# Product Information Sheet

## N-8092

### Syntheseal®/Nonasbestos Gasket Material F729900E59M9

#### DESCRIPTION

N-8092 is used in automotive, small engine, and compressor applications. It has excellent crush resistance at high flange pressures, and excellent sealing properties with oil, fuel, and water. It is intended for applications with short duration maximum temperatures up to 180°C (350°F).

#### SPECIFICATION PROPERTIES

Property	Value	Method
Density, g/cc(lb/cu.ft)	1.20 (75) (min.)	ASTM F 1315
Compressibility, % (at 34.5MPa)	15 - 30	ASTM F 36
Recovery, %	35 (min.)	ASTM F 36
Tensile Strength, AMD, MPa(psi)	11.03 (1600) (min.)	ASTM F 152
Fluid Resistance, IRM903 Oil		ASTM F 146
Change in Tensile Strength, %	30 (max.)	
Change in Thickness, %	20 (max.)	
Change in Compressibility, %	40 (max.)	
Fluid Resistance, Fuel B		ASTM F 146
Change in Thickness, %	20 (max.)	
Change in Weight, %	30 (max.)	
Binder Type	Nitrile Butadiene	

#### REMARKS AND RELATED DOCUMENTS

Specification values determined by the test methods required for ASTM F-104, Type 7 materials.

EnCore®, Hydro-Fused®, MicroPore®, Pro-Formance®, Select-a-Seal®, Syntheseal®, Thermo-Tork®, and Voltoid® are registered trademarks of Interface Solutions, Inc. Select-a-Shield is a trademark of Interface Solutions, Inc.

WARNING: The description and performance data provided herein constitute a material specification for quality control purposes, but do not imply suitability for use in a specific application. Your specific application should not be undertaken without independent study and evaluation for suitability. Failure to select proper sealing products may result in either property damage or personal injury. For specific application recommendations, contact Interface Solutions. INTERFACE SOLUTIONS EXPRESSLY DISCLAIMS ALL WARRANTIES EITHER EXPRESS OR IMPLIED, INCLUDING ANY IMPLIED WARRANTY OF MERCHANTABILITY OR OF FITNESS FOR A PARTICULAR PURPOSE. IN NO EVENT WILL ISI BE LIABLE FOR ANY INDIRECT, SPECIAL, INCIDENTAL, CONSEQUENTIAL OR PUNITIVE DAMAGES, HOWEVER CAUSED AND ON ANY THEORY OF LIABILITY, WHETHER IN CONTRACT, STRICT LIABILITY, OR TORT (INCLUDING NEGLIGENCE OR OTHERWISE) ARISING IN ANY WAY OUT OF THE USE OF THE INFORMATION CONTAINED IN ITS SPECIFICATION DATA SHEETS, ITS PRODUCTS OR THEIR FUTURE USE BY YOU OR ANY THIRD PARTIES, EVEN IF ADVISED OF THE POSSIBILITY OF SUCH DAMAGE.

Form A-5780  
Effective 09/25  
© 2025 Alkegen  
All Rights Reserved

**Alkegen**  
Headquarters  
5215 N. O'Connor Blvd, Suite 2300  
Irving, TX 75039  
Telephone: 716-768-6500  
Website: [www.alkegen.com](http://www.alkegen.com)  
Email: [info@alkegen.com](mailto:info@alkegen.com)