

Product Information Sheet

Insulfrax®

Insulfrax® 1300 HT Anchor-Loc® Modules

Description

Insulfrax® 1300 HT Anchor-Loc® Modules combine the performance features of the proven Anchor-Loc Module attachment systems with the utilisation of new Insulfrax 1300 HT low bio-persistent (LBP) fibre thermal insulation from Alkegen. Insulfrax 1300 HT is manufactured using enhanced fiberization techniques combined with advanced processing technology, offering a 1300°C grade classification and a use limit temperature for applications up to 1200°C. The needled blanket is completely inorganic and retains its strength, flexibility and thermal properties in many working environments without the generation of smoke or fumes. Insulfrax 1300 HT Blanket can be supplied in a variety of thickness and density combinations and to enable its use for a large range of high temperature applications.

Insulfrax 1300 HT combines good tensile strength and excellent resilience making it a natural choice as feed stock for the manufacture of Anchor-Loc Modules. Insulfrax 1300 HT grade Anchor-Loc Modules are typically manufactured from fully edge-stacked or folded Insulfrax 1300 HT Blanket. The fold location may be on the hot face or cold face of the module, subject to client preference. They can be produced in several design configurations. Insulfrax 1300 HT Anchor-Loc Modules are available with a choice of anchoring systems to enable quick, easy and efficient installation, providing an effective engineered solution for various lining applications.

General Characteristics

Insulfrax 1300 HT Anchor-Loc Modules have the following outstanding characteristics:

- High temperature stability (up to 1300°C)
- Low thermal conductivity
- Thermal shock resistance
- Low heat storage
- Lightweight
- Fast installation & selection of attachment systems

Information on other applications available upon request. Any new and/or special use of these products, whether or not in an application listed in our literature, must be submitted to our technical department for their prior written approval.



Typical Applications

Insulfrax 1300 HT Anchor-Loc Modules are the product of choice for a wide range of applications in a number of industries.

- Heat treatment and forge furnaces
- Annealing furnaces
- Process heaters
- Ceramic tunnel kilns and intermittent kilns
- Stress relieving furnaces
- Door and cover linings
- Carbottom heating furnaces
- Stack, flue and duct linings
- Incinerators and boilers
- Ladle preheat stands

ALKEGEN

Product Information Sheet



Insulfrax® 1300 HT Anchor-Loc® Modules

Typical Product Parameters

Insulfrax	1300 HT		
Typical Chemical Analysis (fibre wt. %)			
SiO ₂	72.0 – 78.0		
CaO + MgO	21.0 – 27.0		
Other Oxides	<3.0		
Physical Properties			
Colour	White		
Classification Temperature (°C)*	1300		
Use Limit (°C)*	1200		
Mean Fibre Diameter (microns)	3.6		
Density (kg/m ³)	160 kg/m ³	170 kg/m ³	190 kg/m ³
Thermal Conductivity (W/mK) – ASTM C-201			
Mean Temperature			
200°C	0.09	0.08	0.08
400°C	0.12	0.11	0.11
600°C	0.16	0.15	0.14
800°C	0.20	0.19	0.17
1000°C	0.27	0.25	0.22
1200°C	0.35	0.33	0.28

* The maximum continuous use limit temperature for these products depends upon operating and application conditions, and also the engineered design of the insulation lining. For additional information and support regarding product performance or to identify the recommended product for your application, please contact your nearest Alkegen Application Engineering office.

Data shown is based on average results of tests conducted under standard procedures and are subject to variation.

Product Information Sheet



Insulfrax® 1300 HT Anchor-Loc® Modules

Availability

Module Dimensions (mm)		
Length	Width	Thickness
300mm	300mm	100 to 350mm

Other densities, thicknesses, block sizes may be available on request subject to minimum order requirements.

Anchor systems available include:

RX2 = Side fixing system: Standard grade AISI 321

TL = Thread-Loc. Centre fixing system: Standard grade AISI 304

WL = Weld-Loc: Standard grade AISI 304

Other anchoring systems available subject to request.

Handling Information

A Safety Data Sheet (SDS) has been issued describing the health, safety and environmental properties of this product, identifying the potential hazards and giving advice on handling precautions and emergency procedures. This must be consulted and fully understood before handling, storage or use.

Insulfrax fibre has a high solubility in simulated body fluids and hence carries no hazard classification, meeting stringent European regulatory requirements. Insulfrax 1300 HT fibres are exonerated from classification as hazardous (tested according to Note Q Regulation (EC) No. 1272/2008).

Information contained in this publication is for illustrative purposes only and is not intended to create any contractual obligation. The following are registered trademarks of Alkegen: Insulfrax®

The test data shown are average results of tests conducted under standard procedures and are subject to variation. Results should not be used for specification purposes.

Product Information Sheets are periodically updated by Alkegen. Before relying on any data or other information in this Product Information Sheet, you should confirm that it is still current and has not been superseded. A Product Information Sheet that has been superseded may contain incorrect, obsolete and/or irrelevant data and other information.

Alkegen

Headquarters

5215 N. O'Connor Blvd, Suite 2300
Irving, TX 75039
Telephone: 716-768-6500
Website: www.alkegen.com
Email: info@alkegen.com

European Office

Glasshouse, Alderley Park
Nether Alderley
Cheshire
SK10 4TG
United Kingdom

Customer service email:
customerserviceeurope@alkegen.com